

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
15 September 2005 (15.09.2005)

PCT

(10) International Publication Number  
**WO 2005/084839 A1**

(51) International Patent Classification<sup>7</sup>: B09B 3/00, B29B 17/02, B01J 8/10, C08F 8/50, C22B 7/00, B03B 9/06, B02C 19/18, 17/00, 17/16

(21) International Application Number:  
PCT/SK2005/000004

(22) International Filing Date: 2 March 2005 (02.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
PP 0133-2004 8 March 2004 (08.03.2004) SK

(71) Applicant and

(72) Inventor: MADAR, Ivan [SK/SK]; Krizna 12, 811 07 Bratislava (SK).

(72) Inventor: JURIGA, Martin; A. Halasu 651/22, 026 01 Dolny Kubin (SK).

(74) Agent: HOLOUBKOVA, Maria; Holoubkova Patent and Trademark Agency, Dostojevského rad 1, 811 09 Bratislava (SK).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Declaration under Rule 4.17:**

— of inventorship (Rule 4.17(iv)) for US only

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF PROCESSING MULTICOMPONENT, COMPOSITE AND COMBINED MATERIALS AND USE OF SO SEPARATED COMPONENTS

(57) Abstract: The nature of the method of treating multicomponent, composite and combined materials, consisting of organic and inorganic, non-metallic and metallic components and especially of waste from electronic and electric devices and equipments, consists in that the treated materials are pretreated by removing contaminating components containing toxic heavy metals and polychlorinated biphenyls, by grinding the waste to particles having the size of 5 to 25 µm at most, and they are subjected, in an inert or reducing environment at a temperature of 350 °C to 600 °C and at a pressure of 100 kPa to 10 MPa, to the action of blades of a rotational mechanism for 10 seconds to 10 minutes, and to the action of a moving bed of solid particles of a substance, performing whirling motion. In this way there occurs depolymerization, cracking and state transformation of macromolecular, solid and liquid organic fractions and their separation from the composite material in the form of organic vapours and gases, and disintegration of inorganic non-metallic fractions to small particles and increase of metal concentration in the inorganic phase.



WO 2005/084839 A1

METHOD OF PROCESSING MULTICOMPONENT, COMPOSITE AND COMBINED MATERIALS AND USE OF SO SEPARATED COMPONENTS

### Technical Field

Present invention concerns a method of processing multicomponent, composite and combined materials, and use of so separated components by effective separation of metals and other inorganic fractions comprising the multicomponent, composite material, from organic fractions by depolymerisation and decomposition of organic fractions and their separation in the form of vapours and gases.

### Background Art

Some waste materials, originating from electric and electronic equipment and devices (WEEE – waste electric and electronic equipment), for example printed circuit boards, integrated circuits, microchips, memory modules and other parts of electronic scrap have complicated composite structure, which presents a significant problem from the point of view of treating such waste material. Such composite waste materials contain valuable materials integrated with troublesome and dangerous substances in close proximity and must be processed separately for utilization or disposal. Nonferrous metals like copper, tin or lead, constitute a valuable component of electronic scrap, the content of these metals reaching up to 35 % of the scrap weight. The electronic scrap often contains also noble metals, in particular silver, gold, platinum and palladium, wherein the noble metal content in some types of "high grade" integrated circuits may reach up to 0.3 %.

On the other hand, complicated kinds of electric and electronic scrap often comprise troublesome and dangerous substances. Ceramics and plastics represent further components, constituting the waste, and they represent about 60 % of their weight. The printed circuit boards, reinforced with glass fibers, often contain halogens, especially bromine, as a component of retardants of plastics and resins combustion. Nonseparated conductors are often isolated by PVC. In some waste materials of the electronic scrap it is possible to identify integrated capacitors, containing PCB (polychlorinated biphenyls). It is

obvious that thermal treatment of such waste by standard metallurgical methods in the presence of air oxygen creates a risk of forming dioxins and furans, as well as other dangerous substances. Therefore, because of ecological, but also of economical reasons the metals as well as other valuable components of the composite waste must be separated to a high degree of purity before further utilization, what can be achieved only by extensive disintegration.

A good electronic scrap and composite waste recycling method must allow for separation of individual components in such a way that the obtained metals would contain minimum of non-metallic components and, simultaneously, it must allow recycling also for the organic fractions, especially plastics. From a pure mixture of nonferrous metals it is subsequently possible to obtain by standard metallurgical methods not only the prevailing metal - copper, but also other metals, like zinc, lead, tin, as well as silver, gold, platinum and palladium.

The presently known methods and techniques of treating and recycling multicomponent parts of waste electric and electronic devices and equipments which fulfill the above given criterion, can hardly be accepted from the ecological point of view, or they are economically highly demanding.

The most spread recent techniques of recycling composite and combined electronic scrap are based on physical, especially mechanical principles. The first stage of recycling consists usually of manual dismantling the device or apparatus and detaching simple parts. To eliminate contamination of the other components, it is necessary to remove from the composite parts, especially from the printed circuit boards, batteries containing heavy metals (nickel, cadmium), mercury switches, and PCB containing capacitors. This step is sometimes omitted or it is infeasible because of the component size. The waste composite material is subsequently mechanically disintegrated in several steps, usually in two- to four-rotor crushers, cutters and hammer mills, possibly in granulating machines. Metal iron is separated from the crushed material by a magnetic separator. The obtained crushed material without iron is subsequently sorted with the aim to separate the other metals from

the remainder using various physical procedures. Vibrational sorting machine, sorting in air stream or electrostatic separators are often used. Some valuable individual components are separated from the remainder by flotation or similar methods utilizing the differences in density of the involved components and gravitation.

The products of mechanical recycling consist usually on one hand of concentrates of iron and nonferrous metals including undesired content of residua and organic substances, subsequent treating of which by metallurgical techniques is accompanied by adverse ecological consequences. On the other hand the products of such recycling are predominantly a non-metallic remainder and dust, which, as a consequence of their composition and content of residua, represent nonutilizable waste. The yield of metal recycling using the above classical procedures is limited and, moreover, a part of the noble metals becomes a part of waste, often dangerous, which makes up to 60 % of the original waste composite material. Recycling of organic substances, especially macromolecular substances from composite electric and electronic waste do not belong to the worldwide background art.

Procedure, described by F. Ambrose and B. W. Dunning in the work "Accomplishments in Waste Utilization", 7<sup>th</sup> Mineral Waste Utilization Symposium, Chicago, Oct. 20-21, 1980, Washington, US Department of the Interior, Bureau of Mines, is oriented at recycling military electronic scrap in the form of complete, undismantled switch boxes, as well as individual circuit boards. The waste is disintegrated in several stages in various devices and equipments and after each disintegration stage particles of the corresponding material are separated. Iron particles are separated magnetically and aluminum particles are separated in an eddy current separator. A cylindrical electrostatic separator may be used for treating a mixture of smaller metal particles and non-conducting residua. The final products of this treating procedure are iron, copper, aluminum, further metals and contaminated remainder, containing unseparated metals and residua. The metals may be, if necessary, refined or used directly as a starting raw material. The noble metals may be recovered by hydrometallurgical processes in specialized metal refineries. The residue cannot be usually utilized anymore and it must be treated as dangerous waste.

According to the method, described by K. O. Tillman in the work "Recycling betrieblicher Abfälle" ("Recycling industrial waste"), loose-leaf edition, July 1991, WEKA Fachverlag Kissingen 1990, isolated printed circuit boards, that have been detached from the devices, are first crushed in a two-rotor cutter crusher to particles less than 30 mm. Iron particles are removed from the resulting mixture using a magnetic separator. The remainder is cooled with liquid nitrogen to a temperature of -130 °C, at which the plastic fractions become fragile. The cooled waste is ground in a continually working hammer mill and disintegrated to fine particles. The granulate is separated in a vibrational separator to a metal and a remainder fraction. The powder residue is accumulated and sent to a refinery for recovery of noble metals present. In a specialized metallurgical plant, copper is recovered, and the rare metals, present in the metal fraction, obtained in the anode mud after copper recovery, may be treated in a refinery for rare noble metals. The remaining fractions are not utilizable as raw material.

The above given methods do not ensure sufficient disintegration of the composite material and, moreover, the commonly used separation devices do not achieve sufficient level of separation. A consequence of this is that the metal fraction still contains a relatively high portion of residual materials, among others also halogens, what leads to formation of dioxins and furans during melting of metals. This reduces advantages of metal recycling from waste.

Moreover, the remainder fractions, considered to be waste, still contain 10 to 20 % of metals, which fact may in case of waste thermal treating adversely influence the lifetime of the catalyst used for treatment of combustion gases.

Some disadvantages of the above procedures are eliminated by the methods described in the patent documents US 5,683,040 and US 6,244,054. These methods utilize, as the key operation of disintegration of composite materials, cryogenic treatment of the composite material, from which batteries, switches and capacitors, which contain harmful substances, are removed before the cryogenic treatment, and the material is ground to

smaller particles. Liquid nitrogen is used as the cryogenic substance. Embrittled overcooled particles are discontinuously ground in a hammer mill, where the ground material is simultaneously separated on sieves into a fine and a coarse fraction. Coarse metallic fraction can be discontinuously taken away from the device. Of this fraction iron can be separated in a magnetic separator. The fine fraction is sorted based on the particle size into several narrow subfractions, which may be independently separated in a corona-roller separator in metallic and residual non-metallic particles. In the procedure, described in US 6,244,054, supercooling the composite material in a cooling tank is optimized by adding it in discrete doses and by discontinuous withdrawing the supercooled material for grinding, whereby optimization of the liquid gas consumption, reduction in energy consumption, minimization of necessary human labor and working time are achieved.

Although the latter procedures yield metal concentrates of high purity, residual fractions with low content of metals, and they minimize emissions from the recycling process, they have a disadvantage that, in consequence of energy demandingness of cryogenic techniques, they approach the limits of economical acceptance because of high operation costs. Moreover, they do not allow utilization and recycling of non-metallic residues, especially organic fractions present in the composite materials.

Also known is the method of treating low-grade organic substances according to the SK patent No. 279 397, the nature of which consists in that the low-grade organic substances are subjected, at a temperature of 150 °C to 700 °C and at a pressure of 0.1 MPa to 2.5 MPa, to the action of a moving bed of solid particles which perform whirling motion, whereby the solid particles of a substance constituting the moving bed are set in whirling motion by intensive stirring.

The aim of the present invention is to eliminate disadvantages of the methods used so far, especially of the methods of recycling electric and electronic scrap, in which the key operation is disintegration of composite material.

### Disclosure of Invention

The nature of the method of treatment of multicomponent, composite and combined materials, consisting of organic and inorganic, non-metallic and metallic components and especially of waste from electronic and electric devices and equipments, consists in that the treated materials are modified by removing contaminating components containing toxic heavy metals and polychlorinated biphenyls by grinding the waste to particles having the size of 5 to 25 mm at most, and they are subjected, in an inert or reducing environment at a temperature of 350 °C to 600 °C and at a pressure of 100 kPa to 10 MPa, to the action of blades of a rotational mechanism for 10 seconds to 10 minutes, and to the action of a moving bed of solid particles of a substance, which perform whirling motion. In this way there occurs depolymerization, cracking and state transformation of macromolecular, solid and liquid organic fractions and their separation from the composite material in the form of organic vapours and gases. Non-metallic, especially ceramic inorganic fractions are disintegrated by the destructive action of blades of the rotational mechanism to small particles, allowing to mechanically release metals from fine inorganic (micro- and nano-) structures of the composite material. Separated and released nonferrous and noble metals, present in the multicomponent material, are able, under the above conditions, to form intermetallic phases, compounds or alloys, thus making further treatment of separated fractions, especially free metals, more effective.

The inert environment, which prevents the present substances from oxidation, is ensured by nitrogen or carbon dioxide or water vapour, or gaseous products of depolymerization, cracking and state transformation of the macromolecular, solid and liquid organic fractions, which act as inert at the above conditions.

To allow reduction of metals from their compounds present in the composite material the above process may be conducted so that the composite materials are subjected to the action of blades of a rotational mechanism in reducing environment, wherein the reducing environment is formed by hydrogen or a hydrogen releasing substance or gaseous products of depolymerization, cracking and state transformation of the macromolecular, solid and liquid organic fractions, which act as reducing.

To remove halogens and sulfur from an organic phase present in the composite material the above process may be conducted so that the multicomponent, composite and combined materials, consisting of organic and inorganic non-metallic and metallic components, are subjected to the action of blades of a rotational mechanism in alkaline environment. The alkaline environment is ensured by solid particles of an alkaline substance, performing whirling movement, which substance is a solid alkaline absorbent, like calcium oxide or calcium carbonate or calcium hydroxide or sodium hydroxide or potassium hydroxide, in which halogens and sulfur present in the organic fraction of the composite materials are chemically bounded.

The solid particles of a substance, which perform whirling movement, may be formed partially or fully by a substance which acts under the reaction conditions catalytically on the running cleaving chemical reactions or it may be a substance which is inert under the reaction conditions to the present reacting substances, such as granular quartz and/or silica sand and/or aluminosilicates and/or other natural and/or synthetic minerals, containing silicon and/or aluminum and/or calcium and/or sodium and/or potassium and/or oxygen and/or sulfur. The solid particles of a substance, which perform whirling movement, may be formed partially or fully by a substance, which results from disintegration of inorganic non-metallic fractions of the multicomponent, composite and combined materials to small particles, and by metal particles, released from the multicomponent, composite and combined materials.

Products of treatment of composite materials according to the present method are on one hand organic gaseous and liquid hydrocarbons of medium and/or high boiling range, which are withdrawn from the process in the condensation part of the device and can be utilized in various ways, most simply as a source of thermal energy. On the other hand finely ground solid phase is withdrawn from the device from which phase all organic and volatile substances, including water, are removed and which contains all inorganic components, i. e. metals and non-metals present in the original composite material. In consequence of organic substances removal, the content of which in composite materials



usually ranges from 35 to 50 % by weight, concentration of metals in the inorganic phase is increased, thus making the subsequent operations oriented to metal recovery more effective. The primary metal concentrate can be valuated by various methods with the aim to recover present nonferrous and noble metals. Metals as forgeable material are not fragile, and therefore, during the action of the blades of a rotational mechanism they are not liable to disintegration. This fact may preferably be utilized for separation of nonferrous metals, especially of copper and aluminum, from noble metals. Nonferrous metals occur in greater particles, while noble metals are mostly finely dispersed. Sorting the primary concentrate on sieves may lead to separation of the coarse fraction with prevailing content of copper and aluminum from a fine fraction or fine fractions of various granulometry with prevailing content of noble metals. Further increase of metal content can be achieved in granulometrically-separated fractions by separation of inorganic particles using a corona-roller separator. This may be done also with the primary metal concentrate. The primary metal concentrate or granulometrically sorted fractions, possibly fractions, from which inorganic substances have been removed in a corona-roller separator, are suitable for final recovery and refining metals by classical thermal metallurgical processes, for example by means of lead in a shaft furnace, possibly in an English furnace, or by chemical metallurgical processes, the so called wet process, for example by successive dissolving the noble metals using solutions of cyanides, aqua regia, hydrochloric acid etc.

Using the above procedure metals are concentrated and inorganic fractions are separated from the organic fractions, comprising the multicomponent, composite and combined material.

The respective separated organic, gaseous and liquid fractions may be used to produce alternative fuels, and the inorganic components, like the metal concentrate, may be used for metallurgical treatment, wherein the inorganic fraction will be divided according to the particle size to finer and coarser components by sorting on sieves and from the so obtained fractions non-metallic particles will be removed in an electrostatic separator.

The method of the present invention allows, for example, economically and ecologically advantageous recycling of waste electric and electronic devices and equipments or their parts, for example waste printed circuit boards, microchips and integrated circuits, memory modules and other complicated kinds of electric and electronic scrap.

#### Example of embodiment of the invention

In an operating research equipment BLOWDEC, built according to the SK patent No. 279 397 with the input power of 45 kW a whirling moving bed has been created, the solid particles of which comprised common silica sand. After heating to 450 °C crushed electronic scrap has been continuously fed to the reaction chamber using a screw conveyer. The electronic scrap has consisted mainly of a mixture of ground waste printed circuits from dismantled amortized computer equipments. Batteries and greater capacitors have been removed from the printed circuits before grinding in a cutter mill. The size of the ground particles was up to 10 mm and iron particles have been removed from the ground material in a magnetic separator.

Simultaneously, water vapour has been fed to the reaction chamber as an inert medium in an amount of 0.75 % of the batch weight. In the reaction chamber with whirling moving bed, cleaving and depolymerizing reactions of plastics and resins, which formed a part of the electronic scrap, took place at a temperature of 450 °C and at a pressure of 120 kPa. Gaseous reaction products have been lead to the condensation part of the BLOWDEC device and here intensively cooled in a raschig rings filed quench condenser. Heavy gas oil has been used as the primary cooling medium. Simultaneously, the crushed inorganic phase has been continuously withdrawn from the process chamber by means of a discharging device.

The solid phase has been analyzed with the aim to determine the content of relevant metals and major inorganic additives. The metal content has been determined by the AAS method and X-ray fluorescence analysis. The gaseous and liquid product have been analyzed using standard procedures, used in crude oil analysis. Quality, composition and properties of the products are given in Tables I and II.

Table I

Content of essential inorganic substances in the solid phase

Substance	Unit	Value
SiO <sub>2</sub>	% by weight	34.1
Al <sub>2</sub> O <sub>3</sub>	% by weight	29.1
Copper - Cu	% by weight	14.5
Lead - Pb	% by weight	2.8
Tin - Sn	% by weight	4.8
Iron - Fe	% by weight	5.5
Zinc - Zn	% by weight	0.5
Gold - Au	ppm (% by weight)	650 (0.065)
Platinum - Pt	ppm (% by weight)	400 (0.040)
Palladium - Pd	ppm (% by weight)	160 (0.016)
Silver - Ag	ppm (% by weight)	1200 (0.120)
Carbon - C	% by weight	2.9

The overall content of noble metals (except silver) in the unsorted inorganic fraction has been 0.121 % by weight, representing an amount of 1.21 kg in 1 ton of the inorganic product.

Table II

Quality of the liquid product

Parameter	Unit	Value
Density at 20 °C	kg.m <sup>-3</sup>	886
Viscosity at 40 °C	mm <sup>2</sup> s <sup>-1</sup>	19.2
Content of mechanical impurities	% by weight	0.16
Water content	% by weight	0.08

Ash content	% by weight	0.21
Inflammation point	°C	61
Solidification point	°C	18
Heating value	MJ/kg	42.1

The liquid hydrocarbon condensate has constituted 31.4 % by weight of the overall weight of organic substances of the batch of electronic scrap. The residue of 2.5 % by weight has comprised gases (methane, light hydrocarbons up to C<sub>5</sub>, and CO<sub>2</sub>), which could not condensate under the conditions created in the condensation system of the technological device.

#### Industrial applicability

Method of the present invention can be utilized in the industrial area of waste economy, oriented to preferred utilization and valuation of waste as a source of raw materials. The invention allows an economically and ecologically advantageous recycling waste electric or electronic devices and equipments, or their multicomponent, composite and combined parts, for example printed circuit boards, integrated circuits, microchips, memory modules and the like, as well as other complicated kinds of electric and electronic scrap.

## C L A I M S

1. Method of processing multicomponent, composite and combined materials, consisting predominantly of waste materials from electronic and electric devices and equipments, and use of separated components, under the action of a moving bed of solid particles of a substance, performing whirling movement, characterized in that the treated materials are pretreated by removing contaminating components containing toxic heavy metals and polychlorinated biphenyls by grinding the waste to particles having the size of 5 to 25 mm at most, and they are subjected, in an inert environment at a temperature of 350 °C to 600 °C and at a pressure of 100 kPa to 10 MPa, to the action of blades of a rotational mechanism for 10 seconds to 10 minutes, wherein there occurs depolymerization, cracking and state transformation of macromolecular, solid and liquid organic fractions and their separation from the composite material in the form of organic vapours and gases, and disintegration of inorganic non-metallic fractions to small particles and increase of metal concentration in inorganic phase.
2. Method according to claim 1, characterized in that after removing the contaminating components containing toxic heavy metals and polychlorinated biphenyls and before the treatment in inert environment by the action of blades of a rotational mechanism iron parts are removed in a magnetic separator.
3. Method according to claims 1 and 2, characterized in that the treated materials are subjected to the action of blades of a rotational mechanism in the presence of lead and/or tin and/or zinc and/or mercury, added to the treatment process in an amount of 2 to 50 % by weight.

4. Method according to claims 1 to 3, characterized in that the treated materials are subjected to the action of blades of a rotational mechanism in a reducing environment.
5. Method according to claims 1 to 3, characterized in that the treated materials are subjected to the action of blades of a rotational mechanism in an alkaline environment.
6. Method according to claim 1, characterized in that the inert environment is formed by nitrogen and/or carbon dioxide and/or water vapour and/or gaseous products of depolymerization, cracking and state transformation of the macromolecular, solid and liquid organic fractions, which are inert or act as inert under the above conditions.
7. Method according to claims 1 to 4, characterized in that the reducing environment is formed by hydrogen and/or hydrogen releasing substances and/or gaseous products of depolymerization, cracking and state transformation of the macromolecular, solid and liquid organic fractions, which act as reducing.
8. Method according to claims 1 to 3 and 5, characterized in that the alkaline environment is formed by solid particles of a substance, performing whirling movement and acting as alkaline, which substance is a solid alkaline absorbent, like calcium oxide and/or calcium carbonate and/or calcium hydroxide and/or sodium hydroxide and/or potassium hydroxide.
9. Method according to claims 1 to 3, characterized in that the solid particles of a substance, performing whirling movement, are formed partially or fully of a substance which acts under the reaction conditions catalytically on the running chemical reactions or it is a substance which is inert under the reaction conditions to the present reacting substances, such as

granular quartz and/or silica sand and/or aluminosilicates and/or other natural and/or synthetic minerals, containing silicon and/or aluminium and/or calcium and/or sodium and/or potassium and/or oxygen and/or sulfur.

10. Method according to claims 1 to 3 and 9, characterized in that the solid particles of a substance, performing whirling movement, are formed partially or fully of a substance which results from disintegration of inorganic non-metallic fractions of the multicomponent, composite and combined materials to small particles and metal particles.
11. Utilization of separated organic, gaseous and liquid fractions according to claims 1 to 10 for production of alternative fuel and of the inorganic components as metal concentrate for metallurgical treatment.

# INTERNATIONAL SEARCH REPORT

International Application No  
PC/7SK2005/000004

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B09B3/00 B29B17/02 B01J8/10 C08F8/50 C22B7/00  
B03B9/06 B02C19/18 B02C17/00 B02C17/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B03B B02C B09B B29B C08F C22B C08J B01J C10B C10G C10L H05K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98/39368 A (MADAR, IVAN) 11 September 1998 (1998-09-11) the whole document -----	1,11
A	EP 1 008 395 A (MATSUSHITA ELECTRIC INDUSTRIAL CO., LTD) 14 June 2000 (2000-06-14) paragraphs '0028! - '0043!; claims 1-22 -----	1,11
A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 08, 30 June 1999 (1999-06-30) & JP 11 076980 A (HITACHI LTD), 23 March 1999 (1999-03-23) abstract ----- -/--	1,11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

25 May 2005

Date of mailing of the international search report

06/06/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, fx. 31 651 epo nl,  
Fax: (+31-70) 340 3016

Authorized officer

Leitner, J



# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/SK2005/000004

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 07, 31 July 1996 (1996-07-31) & JP 08 071521 A (HITACHI CHEM CO LTD), 19 March 1996 (1996-03-19) abstract	1, 11
A	----- PATENT ABSTRACTS OF JAPAN vol. 1997, no. 02, 28 February 1997 (1997-02-28) & JP 08 274461 A (SONY CORP), 18 October 1996 (1996-10-18) abstract	1, 11
A	----- US 5 631 346 A (DECKERS ET AL) 20 May 1997 (1997-05-20) -----	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/SK2005/000004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9839368	A	11-09-1998	SK 28297 A3	08-04-1998
			AU 3472497 A	22-09-1998
			CA 2283138 A1	11-09-1998
			CZ 9903116 A3	15-12-1999
			DE 19782262 T0	27-04-2000
			GB 2337265 A ,B	17-11-1999
			JP 2001514680 T	11-09-2001
			NO 994251 A	02-09-1999
			RU 2181126 C2	10-04-2002
			WO 9839368 A1	11-09-1998
			US 6165349 A	26-12-2000
-----				
EP 1008395	A	14-06-2000	JP 2000294919 A	20-10-2000
			JP 2001049355 A	20-02-2001
			JP 2001050518 A	23-02-2001
			CN 1433851 A	06-08-2003
			CN 1260250 A ,C	19-07-2000
			EP 1008395 A2	14-06-2000
			JP 2000301131 A	31-10-2000
			US 6336601 B1	08-01-2002
			US 2001030251 A1	18-10-2001
-----				
JP 11076980	A	23-03-1999	NONE	
-----				
JP 08071521	A	19-03-1996	NONE	
-----				
JP 08274461	A	18-10-1996	JP 3374591 B2	04-02-2003
-----				
US 5631346	A	20-05-1997	DE 4437754 A1	25-04-1996
			AT 161856 T	15-01-1998
			DE 59501212 D1	12-02-1998
			EP 0709404 A1	01-05-1996
			ES 2110808 T3	16-02-1998
-----				